

# Product Data Sheet

#### WS0023

### Greyfell Sandstone (Antique)











## Description

Product Name:	Antique Greyfell Sandstone
Appearance:	A sedimentary sandstone that has naturally varying predominantly grey tones. Naturally riven, split surface finish with hand-dressed tapered edges; then tumbled to give softer surfaces and edges to affect a time worn appearance.
Product Type:	A medium grained, hard sandstone, predominately consists mainly of Quartz; with lesser amounts of Feldspar, Mica and other minerals. The grains are cemented by siliceous and ferruginous materials.
Area of Origin:	Rajasthan, India
Governing Standards:	All data, where relevant, to be established in accordance with BS EN 1341:2012.

## **Physical Properties**

Nominal Sizes (as laid including joints):	Project Pack 900 x 600 x 22mm (16No. per pack) 600 x 600 x 22mm (16No.) 600 x 300 x 22mm (16No.) 300 x 300 x 22mm (12No.)
Size Tolerances:	Length +/- 10mm Width +/- 10mm Thickness +/-3mm
Water Absorption:	1.06% (maximum)
Slip/Skid Resistance:	Satisfactory - low potential for slip 40 USRV Wet (minimum) 65 USRV Dry (minimum)
Abrasion Resistance:	16.30mm (maximum)
Flexural Strength:	36.55MPa (minimum)
Durability:	Frost resistant

### Design Guidance

Indoors or outdoors - domestic and light commercial pedestrian use only. For indoor use, we'd recommend the use of a proprietary sealer, appropriate for your specific needs.

Paving should be laid on a full mortar bed with largest face uppermost with 10-15mm joints. For more installation advice, please refer to our Planning, Install & Care Guide on our website – <u>www.westminsterstone.com/antique-greyfell-</u> <u>sandstone</u>

For a layout example, please refer to our Laying Guides section on our website product page: <u>www.</u> <u>westminsterstone.com/antique-greyfell-sandstone</u>

De-icing salts will not affect the durability of the paving but it can discolour the paving so the surface should be thoroughly cleaned once the need for de-icing salts has receded. Be aware, de-icing salts may damage your pointing depending on the type of pointing product/method. There are chemical granules on the market that act in the same manner and will not damage any surfaces, they also purport to be much cleaner and environmentally friendly.

#### Accessories

We have Hand Cut Greyfell Cobbles & Setts, and a variety of other Greyfell paving ranges with contrasting finishes.

In addition, we have a range of Garden Gravels, Garden Features and Garden Path Edgings that compliment this paving range to achieve that finishing touch.

## Supply

M<sup>2</sup>, No. & Weight per pack:

4 size project pack = 18.9 M<sup>2</sup> = 60No. mixed / 950KG

Packaging:

All packs are crated, suitable for FLT or crane off-load.

Suitability:

Colour Variation:Each piece of stone and each batch of stone is unique. During<br/>install, use product from multiple pallets to ensure a natural<br/>blend, even if your packs are batch matched. Any slabs with<br/>characteristics that are not to your liking, either use for cuts<br/>or install in a more inconspicuous area.Please note:Due to the nature of the product and their transportation<br/>methods, scuffing and scratch marks may be visible on the<br/>surface of units following transportation and handling. If such<br/>marks are apparent, they will weather away naturally due to<br/>the through colour nature of the product.The product is washed after calibration, but some individual<br/>slabs or batches may still be affected by the dusty by-product

## Further Information

of the process. This will clean off with light washing.

Cleaning and Maintenance: For more detailed advice, please refer to our Planning, Install & Care Guide on our website - www.westminsterstone.com/ antique-grevfell-sandstone Generally, cleaning with soapy water and a broom is adequate in most conditions. Inappropriate use of power washers may damage your pointing. If using a power washer, we'd recommend fitting a rotary cleaning head for the most efficient results We strongly recommend against the use of hydrochloric acidbased cleaners. In most domestic settings, there is no real need to seal or impregnate your paving. Regular cleaning and maintenance are usually sufficient. Before applying any chemical cleaners or sealants, we strongly recommend taking advice from the manufacturer of the chemical to ensure it is appropriate for your paving, even then, always test an inconspicuous area first before widespread use to ensure a satisfactory outcome. Sweep leaves regularly. Gathered leaves can guickly decompose and leach tannins that may discolour all hard landscape products. They also encourage algae bloom and other organic growths.

Efflorescence is a calcium carbonate condition associated with cement-based products, not directly with natural sandstone, but on occasion it can migrate through the stone from the mortar bed and display on the drying surface, i.e., paving surface. This can display as a white powdery solid on the surface or just a general dulling of the colours. This is an industry-wide phenomenon and will dissipate gradually with natural weathering. There are proprietary cleaners on the market that can accelerate the removal but always take advice from the manufacturer of the chemical before use. It tends to bloom most commonly in Spring and Autumn seasons but can occur at any time of year given the right climatic conditions. It is very unusual for it display after the first cycle of the seasons.

Sandstone can contain natural salts that display and weather similarly to efflorescence.

Always ensure your paving is free of efflorescence or salt before considering applying a sealant or impregnators. There are coatings that purport to be 'breathable', that allow the migration of carbonates through them so can be applied soon after install. Always take advice and get assurances from the chemical manufacturer that it is appropriate for your stone and construction-type.

Whilst uncommon, weathering and site conditions can cause new shade variation and patches to appear, sometimes in the form of mineral content as it naturally displays, e.g., iron content can oxidise with rusty coloured patches.

Weathering: It should be appreciated that with all products can display weathering characteristics and individual site conditions can cause shade variation to appear across the surface of individual units. Some maintenance is recommended on all sites and all products. Lighter colours tend to show dirt and darker staining agents more clearly than darker colours, alternatively, darker colours may show lighter staining agents more. Algae, lichens, other organic growths and organic staining can affect any surface in an external environment

All hard landscaping products can exhibit surface discolouration when soiled or contaminated.

Product Evolution & Specification: We are continually improving our product design and processes and information is subject to change without notice. We reserve the right to change specification without notice. All sizes, coverages and weights are approximate and subject to tolerances.

# westminster Stone

Westminster Stone Shaws Estate Sodylt Ellesmere Shropshire SY12 9EL

01978 710685 ask@westminsterstone.com westminsterstone.com

Further advice is available on our website at westminsterstone.com

Should you require any further information or assistance, please, do not hesitate to contact us on 01978 710685 or ask@westminsterstone.com.